

SILVER STAR® 015 Aluminum Pigment

PRODUCT DESCRIPTION

SILVER STAR 015 is a medium fine particle size silver dollar pigment. It offers a bright face with a dark flop and average sparkle. This product is recommended for use in high quality automotive finishes and on automotive component parts where good hiding and improved chromatic pigment development are required.

Regular Purity
Non-leafing
Silver Dollar
OEM/Refinish

PRODUCT APPLICATION

SILVER STAR 015 is applicable for use in automotive OEM, refinish, parts and accessories, and interiors. It performs well in both electrostatic Bell and air assisted applications. It is recommended for base coat/clear coat finishes resulting in high gloss.

TECHNICAL DATA

| | |
|-------------------------------------|--|
| Grade | 400 mesh grade |
| Screen Analysis (Max Retained) | 0.01% |
| Non-Volatile By Weight (Target) | 70% by weight |
| Non-Volatile By Volume (Calculated) | 41.7% |
| Particle Size-Microns (Target) | 15 |
| Specific Gravity | 1.58 |
| Weight Volume (lbs/gallon) | 13.16 |
| Bulking Gallons Pounds | 0.076 |
| Solvent | Mixture of mineral spirits and high aromatic |

INCORPORATION GUIDELINES

The paste should be pre-soaked in a solvent at a paste:solvent ratio of between 1:1 to 3:1. Pre-soaking generally takes from one to eight hours. Finer grades typically take longer than coarser grades. Use low shear, slow speed mixing to achieve a smooth consistency free of agglomerates. High shear dispersion techniques should be avoided, as they will distort the aluminum flakes.

SAFETY AND HANDLING

Aluminum pigment should be stored in the original shipping container and kept tightly sealed. Store containers in a cool, dry, well-ventilated, and properly rated area. Avoid any conditions that will suspend or float the particles in the air, creating a dust cloud. Avoid all possible sources of ignition. For additional information, please refer to the MSDS for this product, available from Silberline upon request. A Material Safety Data Sheet is supplied with all samples of this grade.

All statements, information and data presented herein are believed to be accurate and reliable but are not to be taken as a guarantee, express warranty or implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which seller assumes legal responsibility, and they are offered solely for your consideration, investigation and verification. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent. Copyright 2010-2012 Silberline Manufacturing Co., Inc. All Rights Reserved.